



PIPELINE[®]
PLASTICS

ENERGY PE4710

APPLICATIONS

Pipeline Plastics ENERGY Pipe is a PE 4710 high performance bimodal high density polyethylene (HDPE) pipe designed for Oil & Gas Gathering, Multi-Phase Fluids, Raw Water, Brine Water, Coal Bed Methane, Landfill Methane and Leachate. It has superior toughness and resistance to the harsh environments found in these demanding applications.



CONFORMANCE

- ASTM F2619 Standard Specification for High-Density Polyethylene (PE) Line Pipe
- API 15LE Specification for Polyethylene Line Pipe (PE)
- Cell Classification PE445574C per ASTM D3350
- Plastics Pipe Institute (PPI) TR-4 Listing as PE4710 (also meets PE3408 per D3350-02a)
- Hydrostatic Design Basis 1,600 psi @ 73°F (23°C) and 1,000 psi @ 140°F per ASTM D2837
- Color & UV Stabilizer: (C) Black with 2% min Carbon Black per ASTM D3350
- Heat fusion procedure according to ASTM F2620, and PPI TR-33 and TR-41
- Installation is recommended to follow PPI Handbook of Polyethylene Pipe, 2nd Ed.
- Leak testing should be performed according to ASTM F2164, "Standard Practice for Field Leak Testing of Polyethylene (PE) and Crosslinked Polyethylene (PEX) Pressure Piping Systems Using Hydrostatic Pressure." Appropriate safety considerations should always be followed.

Corporate Headquarters

1301 Solana Blvd., Bldg. 1 Suite 1440, Westlake, TX 76262
O: 817-693-4100 F: 817-693-4101



PIPELINE
PLASTICS

ENERGY PE4710 TECHNICAL DATA

| Physical Properties | Nominal Value* | Test Method |
|-------------------------------------|-------------------------|-------------|
| Density | 0.960 g/cm ³ | ASTM D1505 |
| Melt Index (MI) 190°C/2.16kg | 0.07 g/10 min | ASTM D1238 |
| High Load Melt Index (190°C/21.6kg) | 7 - 16 g/10 min | ASTM D1238 |
| SCG Resistance (PENT) | 500 hours | ASTM F1473 |
| Tensile Stress @ Yield | 3,500 psi | ASTM D638 |
| Tensile Stress @ Break | 5,000 psi | ASTM D638 |

| Physical Properties | Nominal Value* | Test Method |
|-------------------------------|---------------------------------|-------------|
| Elongation @ Break | >500 % | ASTM D638 |
| Flexural Modulus (2% secant) | 150,000 psi | ASTM D790 |
| Brittleness Temperature | < -103 °F | ASTM D746 |
| Hardness | 62 Shore D | ASTM D2240 |
| Vicat Softening Temperature | 256 °F | ASTM D1525 |
| Thermal Expansion Coefficient | 1.0 x 10 ⁻⁴ in/in/°F | ASTM D696 |

| Nominal Pipe Sizes | | DR 7 | | | DR 9 | | | DR 11 | | | DR 13.5 | | | DR 17 | | |
|--------------------|-----------------|----------|----------|---------|----------|----------|---------|----------|----------|---------|----------|----------|---------|----------|----------|---------|
| IPS Size | Nominal OD (in) | Min Wall | ID (avg) | Wt / Ft | Min Wall | ID (avg) | Wt / Ft | Min Wall | ID (avg) | Wt / Ft | Min Wall | ID (avg) | Wt / Ft | Min Wall | ID (avg) | Wt / Ft |
| 1 ¼" | 1.660 | 0.237 | 1.157 | 0.462 | 0.184 | 1.269 | 0.375 | 0.151 | 1.340 | 0.314 | 0.123 | 1.399 | 0.260 | | | |
| 1 ½" | 1.900 | 0.271 | 1.325 | 0.607 | 0.211 | 1.452 | 0.491 | 0.173 | 1.534 | 0.411 | 0.141 | 1.602 | 0.341 | | | |
| 2" | 2.375 | 0.339 | 1.656 | 0.948 | 0.264 | 1.816 | 0.767 | 0.216 | 1.917 | 0.643 | 0.176 | 2.002 | 0.532 | 0.140 | 2.079 | 0.431 |
| 3" | 3.500 | 0.500 | 2.440 | 2.058 | 0.389 | 2.676 | 1.663 | 0.318 | 2.825 | 1.394 | 0.259 | 2.950 | 1.160 | 0.206 | 3.064 | 0.935 |
| 4" | 4.500 | 0.643 | 3.137 | 3.400 | 0.500 | 3.440 | 2.751 | 0.409 | 3.633 | 2.307 | 0.333 | 3.793 | 1.914 | 0.265 | 3.939 | 1.550 |
| 6" | 6.625 | 0.946 | 4.619 | 7.373 | 0.736 | 5.064 | 5.961 | 0.602 | 5.348 | 4.994 | 0.491 | 5.585 | 4.151 | 0.390 | 5.799 | 3.354 |
| 8" | 8.625 | 1.232 | 6.013 | 12.50 | 0.958 | 6.593 | 10.11 | 0.784 | 6.963 | 8.468 | 0.639 | 7.271 | 7.035 | 0.507 | 7.549 | 5.689 |
| 10" | 10.75 | 1.536 | 7.494 | 19.42 | 1.194 | 8.218 | 15.70 | 0.977 | 8.678 | 13.16 | 0.796 | 9.062 | 10.93 | 0.632 | 9.409 | 8.830 |
| 12" | 12.75 | 1.821 | 8.889 | 27.32 | 1.417 | 9.747 | 22.09 | 1.159 | 10.29 | 18.51 | 0.944 | 10.75 | 15.38 | 0.750 | 11.16 | 12.43 |
| 14" | 14.00 | 2.000 | 9.760 | 32.93 | 1.556 | 10.70 | 26.63 | 1.273 | 11.30 | 22.31 | 1.037 | 11.80 | 18.54 | 0.824 | 12.25 | 14.98 |
| 16" | 16.00 | 2.286 | 11.15 | 43.01 | 1.778 | 12.23 | 34.77 | 1.455 | 12.92 | 29.15 | 1.185 | 13.49 | 24.21 | 0.941 | 14.00 | 19.58 |
| 18" | 18.00 | 2.571 | 12.55 | 54.44 | 2.000 | 13.76 | 44.02 | 1.636 | 14.53 | 36.90 | 1.333 | 15.17 | 30.64 | 1.059 | 15.76 | 24.76 |
| 20" | 20.00 | 2.857 | 13.94 | 67.21 | 2.222 | 15.29 | 54.35 | 1.818 | 16.15 | 45.54 | 1.481 | 16.86 | 37.83 | 1.176 | 17.51 | 30.58 |
| 22" | 22.00 | 3.143 | 15.34 | 81.31 | 2.444 | 16.82 | 65.75 | 2.000 | 17.76 | 55.11 | 1.630 | 18.54 | 45.78 | 1.294 | 19.26 | 37.00 |
| 24" | 24.00 | 3.429 | 16.73 | 96.77 | 2.667 | 18.35 | 78.26 | 2.182 | 19.38 | 65.59 | 1.778 | 20.23 | 54.48 | 1.412 | 21.01 | 44.02 |

* Nominal values are typical results and are not guaranteed or intended to be used as a product specification or engineering values.

** Pressure ratings are dependent upon temperature, environmental, and/or chemical considerations which may require the use of additional service factors. The listed pressure ratings are based on PE 4710 materials with 1,000 psi HDS in water environment at 73°F. See PPI TR-9, "Recommended Design Factors for Thermoplastic Pipe", and PPI Handbook of PE Pipe, Chapter 6 – Design of PE Piping Systems for additional guidance. Maximum design temperature is 140°F. Federal design requirements will take precedence for regulated piping systems.